Rec'd PCT/PTO 15 APR 2005

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization International Bureau



(43) International Publication Date 29 April 2004 (29.04.2004)

(10) International Publication Number WO 2004/036663 A3

(51) International Patent Classification7: 27/00

H01L 51/40,

[GB/GB]; 47 Greenhill Park, Penicuik, Midlothian EH26 9EX (GB).

Bromhead Johnson, Kingsbourne House, 229-231 High

(74) Agent: HANSON, William, Bennett; JY & GW Johnson,

Holborn, London WC1V 7DP (GB).

(81) Designated States (national): JP, US.

(21) International Application Number:

PCT/GB2003/004466

(22) International Filing Date: 14 October 2003 (14.10.2003)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

0224121.4

16 October 2002 (16.10.2002)

(84) Designated States (regional): European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

Published:

with international search report

before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(88) Date of publication of the international search report: 19 August 2004

(72) Inventors; and (75) Inventors/Applicants (for US only): BUCKLEY, Alastair [GB/GB]; Flat 2f2, 92 Montpelier Park, Edinburgh EH10 4NG (GB). WILKINSON, Christopher, Ian


West Mains Road, Edinburgh EH9 3JF (GB).

CROEMISSIVE DISPLAYS LIMITED [GB/GB];

Scottish Microelectronics Centre, The King's Buildings,

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: METHOD OF PATTERNING A FUNCTIONAL MATERIAL ON TO A SUBSTRATE



(57) Abstract: A method of patterning a functional material (150) onto a substrate (100) comprises the steps of (a) applying a layer of protective material (130), soluble in a solvent in which the functional material is insoluble, to at least one major surface of said substrate; (b) removing areas of said layer (130) to gain access to the substrate in well-defined regions; (c) depositing the functional material (150) at least onto the substrate in the well-defined regions; and (d) removing the remaining layer of protective material from the substrate by dissolution in said solvent.